

Standard Steel Pipe

ASTM A53 TYPE E GRADE A Submittal Data Sheet



Scope

Covers black and hot-dip galvanized electric resistance weld Grade A pipe. Pipe is intended for mechanical and pressure applications and is acceptable for ordinary uses in steam, water, gas and air lines. Pipe is suitable for welding and threading. It is produced to the latest revision of ASTM A53/A53M, Federal Specification WW-P404 and ASME B36.10M.

Hot-dip Galvanized

The average weight of zinc coating shall be not less than 1.8 oz. per sq. ft. of surface (inside and outside). When galvanized pipe is bent or otherwise fabricated to a degree that causes zinc coating to stretch or compress beyond the limit of elasticity, some flaking of the coating may occur.

Hydrostatic and Non-destructive Electric Testing

Hydrostatic inspection test pressures for plain-end pipe are listed in Table X 2.2 of the A53/A53M specification. Test pressures shall be maintained for a minimum of five seconds. Non-destructive electric testing of the weld seam is not a requirement on lengths of ERW pipe NPS 1½ and smaller.

Chemical Requirements

Composition, max. %

<u>Carbon</u>	<u>Manganese</u>	<u>Phosphorus</u>	<u>Sulfur</u>	
.25	.95	.05	.045	
<u>Copper*</u>	<u>Nickel*</u>	<u>Chromium*</u>	<u>Molybdenum*</u>	<u>Vanadium*</u>
.50	.40	.40	.15	.08

*The combination of these five elements shall not exceed 1.00%.

Tensile Requirements

TENSILE STRENGTH, MIN.	YIELD STRENGTH, MIN.	ELONGATION IN 2"
48,000 psi	30,000 psi	Refer to A53 table X 4.1

Bending Test (Cold)

NPS	DEGREE OF BEND	DIAMETER OF MANDREL
2 and under	90°	12x pipe OD

Frequency of Tests

Tensile tests are required on one length of pipe from each lot of 500 lengths or fraction thereof for each size.

End Finish

Plain End: End finish shall be at the option of the manufacturer.

Threaded: to ANSI® Standard B 1.20.1

Couplings: to ASTM Standard A 865

Weights and Dimensions

STANDARD (SCH. 40) BLACK PLAIN END

NPS	OD	NOMINAL WALL	WEIGHT
	in.	in.	lbs./ft.
¼	0.540	0.088	0.43
⅜	0.675	0.091	0.57

EXTRA STRONG (SCH. 80) BLACK PLAIN END

NPS	OD	NOMINAL WALL	WEIGHT
	in.	in.	lbs./ft.
¼	0.540	0.119	0.54
⅜	0.675	0.126	0.74

All information contained herein is accurate as known at the time of publication. Wheatland Tube reserves the right to change product specifications without notice and without incurring obligations.

Permissible Variations in Wall Thickness

Minimum wall thickness at any point shall not be more than 12.5% under nominal wall thickness specified.

Permissible Variations in Outside Diameter

Pipe shall not vary more than +/- 0.016" from the standard specified.

Permissible Variations in Weight per Foot.

Pipe shall not vary more than +/- 10% from the standard specified.

Product Marking

Each bundle tag securely attached to the bundle shall show the manufacturer, the grade of pipe (ASTM A53), the kind of pipe (E for electric resistance weld, A for Grade A), the size (XS for extra strong), and the length. Bar coding is acceptable as a supplementary identification method.

SUBMITTAL INFORMATION

PROJECT:

ENGINEER:

LOCATIONS:

CONTRACTOR:

SPECIFICATION REFERENCE:

COMMENTS:

DATE:

SYSTEM TYPE:



1 Council Avenue, P.O. Box 608
Wheatland, PA 16161
P 800.257.8182
F 724.346.7260

info@wheatland.com
wheatland.com
Follow us on Twitter:
@WheatlandTube



Wheatland Tube
A DIVISION OF ZEKELMAN INDUSTRIES

WST-082420