
## **Concrete Insert — ZCIN**

## Concrete Insert Nut

Standard finishes are Electro-Galvanized (EG) and Plain (PL).



CATALOG NUMBER		wт	RS	T (THICKNESS)
PLAIN FINISH	EG FINISH	lbs.		in.
ZCIN0025PL	ZCIN0025EG	O.11	1⁄4"-20	1⁄4
ZCIN0037PL	ZCIN0037EG	0.16	<sup>3</sup> ⁄8"-16	1⁄4
ZCIN0050PL	ZCIN0050EG	0.20	1⁄2"-13	5⁄16
ZCIN0062PL	ZCIN0062EG	0.18	<sup>5</sup> ⁄8"-11	5⁄16
ZCIN0075PL	ZCIN0075EG	0.17	<sup>3</sup> ⁄4"-10	1/2
ZCIN0087PL	ZCIN0087EG	0.15	7∕8"-9	1/2

Material is 1%" (41.3 mm) wide x 1/4" (6.3 mm) thick unless specified. Holes are 1/6" (14.3 mm) diameter, 1/16" (20.6 mm) center to edge on 1/6" (47.6 mm) centers unless specified.

## **Material Specifications and Finishes**

Carbon Steel – ASTM A1011-00 SS GR 33 or ASTM A1011-00CS Type B

EG – Electro-Galvanized. Electroplating deposits zinc on the surface of the steel by electrolysis from a bath of zinc salts. Recommended for relatively dry indoor use. This is the standard coating for most ZI-Strut products. Thickness of applied zinc is between 0.2 mils and 0.5 mils (5.1 μm to 12.7 μm). Coatings on ZI-Strut EG products meet ASTM B633 SC1 Type III. PL—Plain. No coating on the steel except some oil left on the part from the pickle and oil or fabrication process.

Note: Specifications subject to change without notice.

## SUBMITTAL INFORMATION

PROJECT:	CONTRACTOR:	DATE:
ENGINEER:	SPECIFICATION REFERENCE:	SYSTEM TYPE:
LOCATIONS:	COMMENTS:	ZI-112823
<ul> <li>1600 Ritchie Court</li> <li>Rochelle, IL 61068</li> <li>P 800.257.8182</li> </ul>	info@wheatland.com wheatland.com info@westerntube.com westerntube.com	VHEATLAND TUBE   WESTERN TUBE